



REVONLING RV 8111

Conventional Anti Fouling

PRODUCT DESCRIPTION	A conventional anti fouling for tropical seawater.						
RECOMMENDED USE	On vessels Operating in tropical seawater.						
CHARACTERISTICS	<ul style="list-style-type: none"> • Must not be exposed to the atmosphere for longer than 24 hours before flooded. • Provide protection against fouling for a period up to 18 months. 						
PHYSICAL DATA	<p>Colour Red Brown</p> <p>Gloss level Semi Gloss</p> <p>Volume Solid Approx. 68%</p> <p>Dry Film Thickness 75 microns per coat</p> <p>Number of Coat 1</p> <p>Theoretical Coverage 9 sq.m/ℓ for 75 microns</p> <p>VOC 300 g/ℓ</p> <p>Flash Point 30°C</p> <p>Shelf Life At least 12 months (cool and dry place)</p> <p>Pack Size 20 Kgs</p>						
SURFACE PREPARATION	Prior to coating, previously coated surface must be dry, undamaged and free from all contaminants, including salt deposits.						
APPLICATION DATA	<p>Application Methods</p> <p>Airless Spray</p> <table> <tr> <td>Nozzle Tip</td> <td>Approx. 0.50 mm (0.020 inch)</td> </tr> <tr> <td>Nozzle Pressure</td> <td>10 MPa (approx. 1400 psi)</td> </tr> <tr> <td>Brush or Roller</td> <td>May be used for small areas</td> </tr> </table>	Nozzle Tip	Approx. 0.50 mm (0.020 inch)	Nozzle Pressure	10 MPa (approx. 1400 psi)	Brush or Roller	May be used for small areas
Nozzle Tip	Approx. 0.50 mm (0.020 inch)						
Nozzle Pressure	10 MPa (approx. 1400 psi)						
Brush or Roller	May be used for small areas						

Mixing Ratio	One component
Thinner	REVONER 118
Surface Temperature	Should be 10°C – 49°C, at least 3°C above the dew point to prevent condensation
Drying Time	
Touch Dry	1 hour at 25°C, 30 minutes at 32°C
Over coating	
Minimum	6 hours at 25°C, 4 hours at 32°C
Refloating	
Minimum	6 hours at 25°C, 4 hours at 32°C

SAFETY PRECAUTION

Keep away from heat, spark and Open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use.

Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against topic hazard.

Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building

DISCLAIMER *The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet i*