



REVONFLOOR CLEAR RV 311

Epoxy Polyamide

PRODUCT DESCRIPTION	Solvent – free two pack epoxy polyamide.																																																	
RECOMMENDED USE	Prepare floor repair and mortars undercoat.																																																	
CHARACTERISTICS	<ul style="list-style-type: none">• A hard wearing, good abrasion and impact resistance.• Solvent free, self – levelling, good resistance to wide spectrum of chemical.• Excellent adhesives to concrete, masonry, plasters and other building material.																																																	
PHYSICAL DATA	<table><tr><td>Colour</td><td>Clear</td></tr><tr><td>Gloss Level</td><td>Gloss</td></tr><tr><td>Volume Solid</td><td>100%</td></tr><tr><td>Number of Coat</td><td>1</td></tr><tr><td>Theoretical Coverage</td><td>5 mm thick mortars 10.00 kg/sq.m</td></tr><tr><td>Mixing Ratio</td><td>Base : Hardener = 2 : 1</td></tr><tr><td>Thinner</td><td>Not required</td></tr><tr><td>Pack Size</td><td>20 Kgs</td></tr><tr><td>Shelf Life</td><td>12 months</td></tr><tr><td>Pot Life</td><td>1 hour at 32°C</td></tr><tr><td>Temperature Resistance</td><td>93°C (dry)</td></tr><tr><td>Flash Point</td><td>Base : 25°C Hardener : 48°C</td></tr><tr><td colspan="6">Drying Time</td></tr><tr><td rowspan="2">Substrate Temperature</td><td rowspan="2">Touch dry</td><td rowspan="2">Hard dry</td><td colspan="3">To Top Coat</td></tr><tr><td>Minimum</td><td>Maximum</td><td></td></tr><tr><td>30 °C</td><td>2 hours</td><td>12 hours</td><td>2 hours</td><td>Indefinite</td><td></td></tr></table>					Colour	Clear	Gloss Level	Gloss	Volume Solid	100%	Number of Coat	1	Theoretical Coverage	5 mm thick mortars 10.00 kg/sq.m	Mixing Ratio	Base : Hardener = 2 : 1	Thinner	Not required	Pack Size	20 Kgs	Shelf Life	12 months	Pot Life	1 hour at 32°C	Temperature Resistance	93°C (dry)	Flash Point	Base : 25°C Hardener : 48°C	Drying Time						Substrate Temperature	Touch dry	Hard dry	To Top Coat			Minimum	Maximum		30 °C	2 hours	12 hours	2 hours	Indefinite	
Colour	Clear																																																	
Gloss Level	Gloss																																																	
Volume Solid	100%																																																	
Number of Coat	1																																																	
Theoretical Coverage	5 mm thick mortars 10.00 kg/sq.m																																																	
Mixing Ratio	Base : Hardener = 2 : 1																																																	
Thinner	Not required																																																	
Pack Size	20 Kgs																																																	
Shelf Life	12 months																																																	
Pot Life	1 hour at 32°C																																																	
Temperature Resistance	93°C (dry)																																																	
Flash Point	Base : 25°C Hardener : 48°C																																																	
Drying Time																																																		
Substrate Temperature	Touch dry	Hard dry	To Top Coat																																															
			Minimum	Maximum																																														
30 °C	2 hours	12 hours	2 hours	Indefinite																																														
SURFACE PREPARATION	All surfaces to be coated should be clean, dry and free from contamination. Concrete Allow 28 days for concrete to cure. Remove surface laitance by acid etching, abrasive or scrapping, apply direct.																																																	
APPLICATION DATA	<table><tr><td>Application Methods</td><td colspan="4"></td></tr><tr><td>Trowel</td><td colspan="4">Recommended</td></tr></table>					Application Methods					Trowel	Recommended																																						
Application Methods																																																		
Trowel	Recommended																																																	
SAFETY PRECAUTION	<p>Keep away from heat, spark and Open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use. Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against toxic hazard. Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.</p>																																																	
DISCLAIMER	<p>The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.</p>																																																	