



Product data sheet

REVONCRYL RV 412

Acrylic Primer

PRODUCT DESCRIPTION	A fast drying, acrylic solvent based synthetic primer.																																
RECOMMENDED USE	Primer for protection of steel and concrete, suitable for interior and exterior areas.																																
CHARACTERISTICS	<ul style="list-style-type: none">Fast drying, maybe top coated in 2 hours at 32°C.Can be top coated with acrylic and alkyd finish.Good adhesive with substrate.																																
PHYSICAL DATA	<table><tr><td>Colour</td><td>White and Red Oxide</td></tr><tr><td>Gloss Level</td><td>Satin</td></tr><tr><td>Volume Solid</td><td>Approx. 55%</td></tr><tr><td>Dry Film Thickness</td><td>50 microns per coat</td></tr><tr><td>Number of Coat</td><td>2</td></tr><tr><td>Theoretical Coverage</td><td>11 sq.m/ltr for 50 microns</td></tr><tr><td>Temperature Resistance</td><td>Maximum : 80°C (dry)</td></tr><tr><td>VOC</td><td>441 g/l</td></tr><tr><td>Flash Point</td><td>36°C</td></tr><tr><td>Shelf Life</td><td>At least 12 months</td></tr><tr><td>Pack Size</td><td>20 Kgs</td></tr></table>	Colour	White and Red Oxide	Gloss Level	Satin	Volume Solid	Approx. 55%	Dry Film Thickness	50 microns per coat	Number of Coat	2	Theoretical Coverage	11 sq.m/ltr for 50 microns	Temperature Resistance	Maximum : 80°C (dry)	VOC	441 g/l	Flash Point	36°C	Shelf Life	At least 12 months	Pack Size	20 Kgs										
Colour	White and Red Oxide																																
Gloss Level	Satin																																
Volume Solid	Approx. 55%																																
Dry Film Thickness	50 microns per coat																																
Number of Coat	2																																
Theoretical Coverage	11 sq.m/ltr for 50 microns																																
Temperature Resistance	Maximum : 80°C (dry)																																
VOC	441 g/l																																
Flash Point	36°C																																
Shelf Life	At least 12 months																																
Pack Size	20 Kgs																																
SURFACE PREPARATION	Previous suitable primer coat, dry and free from any contamination.																																
APPLICATION DATA	<table><tr><td colspan="2">Application Methods</td></tr><tr><td>Airless Spray</td><td></td></tr><tr><td>Nozzle Tip</td><td>0.38 – 0.46 (0.015 – 0.018 inch)</td></tr><tr><td>Nozzle Pressure</td><td>10 MPa (approx. 1400 psi)</td></tr><tr><td>Conventional Spray</td><td></td></tr><tr><td>Nozzle Tip</td><td>1.8 – 2.0 mm (0.071 – 0.079 inch)</td></tr><tr><td>Nozzle Pressure</td><td>0.3 MPa (approx. 43 psi)</td></tr><tr><td>Mixing Ratio</td><td>One component</td></tr><tr><td>Thinner</td><td>REVONER 114</td></tr><tr><td>Surface Temperature</td><td>Should be 10°C – 49°C, at least 3°C above the dew point to prevent condensation</td></tr><tr><td>Drying Time</td><td></td></tr><tr><td>Touch Dry</td><td>10 minutes at 25°C, 5 minutes at 32°C</td></tr><tr><td>Trough Dry</td><td>2 hours at 25°C, 1 hour at 32°C</td></tr><tr><td>Over coating</td><td></td></tr><tr><td>Minimum</td><td>2 hours at 25°C, 1 hour at 32°C</td></tr><tr><td>Maximum</td><td>Unlimited (roughened and dry)</td></tr></table>	Application Methods		Airless Spray		Nozzle Tip	0.38 – 0.46 (0.015 – 0.018 inch)	Nozzle Pressure	10 MPa (approx. 1400 psi)	Conventional Spray		Nozzle Tip	1.8 – 2.0 mm (0.071 – 0.079 inch)	Nozzle Pressure	0.3 MPa (approx. 43 psi)	Mixing Ratio	One component	Thinner	REVONER 114	Surface Temperature	Should be 10°C – 49°C, at least 3°C above the dew point to prevent condensation	Drying Time		Touch Dry	10 minutes at 25°C, 5 minutes at 32°C	Trough Dry	2 hours at 25°C, 1 hour at 32°C	Over coating		Minimum	2 hours at 25°C, 1 hour at 32°C	Maximum	Unlimited (roughened and dry)
Application Methods																																	
Airless Spray																																	
Nozzle Tip	0.38 – 0.46 (0.015 – 0.018 inch)																																
Nozzle Pressure	10 MPa (approx. 1400 psi)																																
Conventional Spray																																	
Nozzle Tip	1.8 – 2.0 mm (0.071 – 0.079 inch)																																
Nozzle Pressure	0.3 MPa (approx. 43 psi)																																
Mixing Ratio	One component																																
Thinner	REVONER 114																																
Surface Temperature	Should be 10°C – 49°C, at least 3°C above the dew point to prevent condensation																																
Drying Time																																	
Touch Dry	10 minutes at 25°C, 5 minutes at 32°C																																
Trough Dry	2 hours at 25°C, 1 hour at 32°C																																
Over coating																																	
Minimum	2 hours at 25°C, 1 hour at 32°C																																
Maximum	Unlimited (roughened and dry)																																
SAFETY PRECAUTION	<p>Keep away from heat, spark and Open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use. Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against topical hazard. Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.</p>																																
DISCLAIMER	<p>The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.</p>																																